



## Features

FreeForm Self-Levelling Underlayment (SLU) is polymer-modified cement powder matrix that has high flow characteristics. FreeForm SLUs are typically used to create a flat and smooth surface with excellent technical characteristics and are used prior to installing interior floor coverings. SLUs are very relevant now as the degree of flatness and smoothness required for floor covering products has increased, with vinyl goods becoming thinner and floor tiles becoming larger, for example.

### Key features include:



Thin Layer Application  
Environment friendly



High Workability  
Fast completion of project



Lower Dimensional Shrinkage  
Fewer cracks in concrete



High Adhesion to Substrate  
Less peeling off | High bonding



Slight Flexibility in Material  
Less cracks | Large panel sizes



High Strength  
High durability | Low maintenance cost



Extensively Tested at Factory  
Quality assured



No Contamination  
Better performance



High Consistency of Material  
Peace of mind

## Application

- On mother slab for levelling application
- For renovation works
- Before application of final overlayers

## Appearance

Supplied as single component premixed fortified mortar. Only water has to be added at site

## Specifications

Max. Aggregate Size	Compressive Strength
4 mm	>40 N/mm <sup>2</sup>
Flexure Strength	Bulk Density
>6 N/mm <sup>2</sup>	~1500 kg/m <sup>3</sup>
Wet Density	Water Requirement
~2200 kg/m <sup>3</sup>	~12.5% of weight
Output/Coverage	
~2.2 kg /mm/m <sup>2</sup>	
Work Time	
Minimum 30 minutes. Will be less when temperatures exceed 28°C or humidity less than 50%	

## Application Thickness

We recommend using the SLU material in 0 to 12 mm thickness.

## Base Surface Preparation

The concrete base or other floor bases must be clean, free of dust and grease. The base must be consistent, without loose particles and disaggregation. The foundation should have a minimum tensile strength of 1.5 MPa. The base must be visually dry. Cracks in the base should be repaired. Weak bases must be removed

or restored. The foundation should be ground or blasted and then aspirated.

### Application/Installation Method

Please refer to separate sheet for guidance on application method.

### Curing

The finished surface may be lightly sprayed with water soon after completion of work in case of hot and windy climate, to prevent excess drying out.

### Open to Traffic

24 hours for foot traffic

### Packing

25 kg bag

### Shelf Life

Minimum 3 months from date of packing before opening. Use within few hours of opening. Store in dry conditions.

### Precautions

Should be stored away from moisture or water.

### Applicable Standards

EN 13813 Screed material and floor screeds. Screed material- Properties and requirements.

### Technical Support

☎ 9374001415

✉ support@freeformbyvyara.in

#### Disclaimer

Any recommendations for application techniques are based on experiences. It is advisable to adapt processing techniques and material quantities to the given local conditions and we refer in this context to our general terms of sale and delivery. Hairline crack formation or deformation by shrinkage on principle cannot be excluded with the offered system and thus are not considered as technical defect. Test areas are strongly recommended before usage/execution in larger areas.

#### Health Precautions

This product contains cement and has an alkaline reaction with moisture/water. Adequately protect hands and eyes. In case of contact with eyes consult doctor immediately.

**Interior, Exterior & Industrial Floors | Wall Finishes | Tile Adhesives | Base Materials | Sealant | DIY**